



TEST REPORT

1. NO : CT22-074719E_M1
2. Client
 - Name : PT. CLEAN AND WELL PACK INDONESIA
 - Address : RUKO CIBUBUR TIMES SQUARE JL ALTERNATIF CIBUBUR B4 NO. 17 RT. 001 RW. 010 JATI KARYA, JATISAMPURNA KOTA BEKASI JAWA BARAT, INDONESIA
3. Date of Test : 2022.08.01 ~ 2022.08.17
4. Use of Report : Submission(D&F global food company & Healing FOOD & PT.FRESHENING INDONESIA)
5. Test Sample : WELTOUCH SPUNLACE
6. Test Method
 - (1) Standards and Specifications for Food Utensils, Containers and Packages.




Affirmation	Tested By Name : Chae Won Kim	CW	Technical Manager Name : Ryu Byung Cheol
1. Our report apply only to the standards or procedures identified and to the sample(s) tested unless otherwise specified. 2. The test results are not indicative of representative of the qualities of the lot from which the sample was taken or of apparently identical or similar products. 3. The results of using only a portion of this report cannot be guaranteed. 4. The authenticity of this test report can be checked on KCL website(www.kcl.re.kr) 5. This Test Report is not based on the [Act on Testing and Inspection of Food and Drugs], and does not have any legal effect with regard to such Act.			

2022.08.17

Korea Conformity Laboratories President Jo, Yung Tae

※ 2022.08.25 Modification M1 Tested by : Chae Won Kim, Technical Manager : Ryu Byung Cheol (시료명 영문으로 변경 및 오타 수정
 수정 전 : Weltouch spanrace
 수정 후 : WELTOUCH SPUNLACE)

Result Inquiry : 199, Gasan digital 1-ro, Geumcheon-gu, Seoul, Korea (82-2-2102-2647)



TEST REPORT

No : CT22-074719E_M1

7. Test Results

1) WELTOUCH SPUNLACE

Test Item(s)	Unit	Specifications	Test Method	Test Results	Remark
Residual Lead(Pb)	mg/kg	Not more than 100 (Sum)	(1)	Not detected	-
Residual Cadmium(Cd)	mg/kg	Not more than 100 (Sum)	(1)	Not detected	-
Residual Mercury(Hg)	mg/kg	Not more than 100 (Sum)	(1)	Not detected	-
Residual Chromium VI(Cr ⁶⁺)	mg/kg	Not more than 100 (Sum)	(1)	Not detected	-
Extraction Lead(Pb)	mg/L	Not more than 1	(1)	Not detected	-
Extraction Arsenic(as As ₂ O ₃)	mg/L	Not more than 0.1	(1)	Not detected	-
Extraction Overall migration 4 % Acetic acid	mg/L	Not more than 30	(1)	9	-
Extraction Overall migration Water	mg/L	Not more than 30	(1)	10	-
Extraction Overall migration n-Heptane	mg/L	Not more than 30	(1)	11	-

▶ Material : Regenerated Cellulose

———— End of Report ————

